










THE PURES

Smooth and almost knotless oak parquet





- Smooth and virtually knot-free oak parquet with occasional small knots up to 10 mm and dark streaks permitted.
- 99% sapwood-free.
- End cracks, insect damage, ingrown bark, and mechanical defects are excluded.
- Even color.

14 x 220		
	14 mm	
	3 mm	√ 2
	220 X 600-2200 mm	







14 x 190		
	14 mm	
	3 mm	√ 2
	190 X 600-1900 mm	



10 x 152		
	10 mm	
	3 mm	√ 2
	152 X 600-1900 mm	




14x120HB		
	14 mm	
	3 mm	√ 4
	120 X 600mm	



WOOD DESCRIPTION

WOOD TYPE	Oak Quercus Rubra
SELECTION	AB(C), limited number of "C" planks admitted
KNOTS	Sporadically, small knots up to 10 mm and small dark tannin streaks are permitted.
SAPWOOD	99% sapwood free
COLOR	Egaal van kleur
EXTRA INFO	End cracks, insect damage, ingrown bark, and mechanical defects are excluded.








THE NATURALS

Soft and slightly rustic oak parquet

- Soft and slightly rustic oak parquet with healthy knots up to 30 mm, dead or open knots max. 20 mm (2/plank), sporadic dark streaks, end cracks, or filled cracks are permitted.
- 99% sapwood-free.
- Discoloration, wormholes, and mechanical defects are excluded.
- Natural color.



14 x 190		
	14 mm	
	3 mm	
	190 X 600-1900 mm	



FALKIRK
NAT 019



DUNDEE
NAT 020



BELFAST
NAT 021



PAISLEY
NAT 023



LIVINGSTON
NAT 025



ABERDEEN
NAT 022

WOOD DESCRIPTION

WOOD TYPE	Oak Quercus Rubra
SELECTION	ABC(D) light rustic, limited "D" planks allowed
KNOTS	Healthy knots up to 30 mm, dead or open knots max. 20 mm (2/plank), sporadic small dark tannin streaks, end cracks, or filled cracks are permitted.
SAPWOOD	99% sapwood free
COLOR	Natural color
EXTRA INFO	Discoloration, wormholes, and mechanical defects are excluded.

